Contents lists available at ScienceDirect



Journal of Environmental Chemical Engineering

journal homepage: www.elsevier.com/locate/jece



Highly-efficient degradation of ensulizole using monopersulfate activated by nanostructured cobalt oxide: A comparative study on effects of different nanostructures

Wei-Jie Liu^a, Young-Kwon Park^b, Wei-Hsin Chen^{c,d,e}, Ha Manh Bui^f, Venkata Subbaiah Munagapati^g, Duong Dinh Tuan^a, Jet-Chau Wen^{g,h}, Siming Youⁱ, Wen Da Oh^{j,*}, Kun-Yi Andrew Lin^{a,*}

^a Department of Environmental Engineering & Innovation and Development Center of Sustainable Agriculture, National Chung Hsing University, 250 Kuo-Kuang Road, Taichung, Taiwan

^c Department of Aeronautics and Astronautics, National Cheng Kung University, Tainan 701, Taiwan

^d Research Center for Smart Sustainable Circular Economy, Tunghai University, Taichung 407, Taiwan

^e Department of Mechanical Engineering, National Chin-Yi University of Technology, Taichung 411, Taiwan

^f Department of Environmental Sciences, Saigon University, Ho Chi Minh 700000, Vietnam

g Research Center for Soil & Water Resources and Natural Disaster Prevention (SWAN), National Yunlin University of Science and Technology, Douliou, Taiwan,

Douliou, Taiwan

Editor: T.T. Lim

Keywords:

Sunscreens

Ensulizole

Nanostructure

UV filter

Cobalt

Oxone

^h Department of Safety, Health, and Environmental Engineering, National Yunlin University of Science and Technology, Douliou, Taiwan

ⁱ James Watt School of Engineering, University of Glasgow, Glasgow G12 8QQ, UK

^j School of Chemical Sciences, Universiti Sains Malaysia, 11800 Penang, Malaysia

ARTICLE INFO

ABSTRACT

The most extensively used sunscreen protecting agent, Ensulizole, has been proven to exhibit hormone disrupting effects. To establish efficient processes to destruct Ensulizole in water, SO4 -- involved advanced oxidation processes using monopersulfate (MPS) seem useful. Since cobalt (Co) is the most capable of metal for activating MPS, Co₃O₄ appears as a promising heterogeneous catalyst for activating MPS to degrade Ensulizole. As catalytic activities of metal oxide catalysts are strongly associated with their morphologies, and surficial properties, nanoscale Co₃O₄ with functional nanostructures would be expected as advantageous catalysts for activating MPS. Therefore, three Co₃O₄ materials with distinct nanostructures and shapes were fabricated in this study, including Co₃O₄ cone ball (COCB), Co₃O₄ plate lump (COPL), and Co₃O₄ needle sheaf (CONS). Their surficial properties are also noticeably distinct with different fractions of Co^{2+} , and Co^{3+} , various oxygen vacancies, textural features and surface defects. Through comparing these three nanostructured Co₃O₄ for activating MPS to degrade Ensulizole, CONS exhibits the tremendously higher catalytic activity than COCB and COPL for activating MPS to eliminate Ensulizole completely and rapidly. The E_a value of Ensulizole degradation of CONS is also significantly low as 9.8 kJ/mol, which is the lowest E_a ever reported in literatures. CONS could also retain its catalytic activities over 5 continuous cycles to rapidly degrade Ensulizole. The activation mechanism of MPS by CONS and Ensulizole degradation pathway are also comprehensively elucidated via experimental evidences and the theoretical calculation to offer insightful information of development of Co-based heterogeneous catalysts for Ensulizole degradation.

1. Introduction

Sunscreen protecting agents (SPAs) have been widely consumed nowadays for guarding skin from UV irradiation. While various types of SPAs are available, Ensulizole has been recognized as the most extensively used SPA especially because Ensulizole can efficiently adsorb UVB irradiation, and also frequently coupled with other reagents for preventing UVA irradiation [1,2]. Nonetheless, Ensulizole has been listed as

* Corresponding authors. *E-mail addresses:* ohwenda@usm.my (W. Da Oh), linky@nchu.edu.tw (K.-Y.A. Lin).

https://doi.org/10.1016/j.jece.2022.107137

Received 25 October 2021; Received in revised form 30 December 2021; Accepted 1 January 2022 Available online 4 January 2022 2213-3437/© 2022 Published by Elsevier Ltd.

^b School of Environmental Engineering, University of Seoul, Seoul 02504, Republic of Korea

an emerging contaminant due to its endocrine disrupting effects [3,4]. Therefore, discharge of this water-soluble Ensulizole into water would cause serious threats to the environment and ecology, and it is highly crucial to establish efficient processes to destruct Ensulizole in water. Specifically, Ensulizole has been continuously detected in various water systems. For example, Ensulizole has been found in both influent and effluent of anaerobic and aerobic gray water treatment systems with its concentration could be ca. of 4.9 μ g/L [5] whereas the concentration of Ensulizole about 1.8–836.3 ng/L has been also detected in surface waters [6].

As advanced oxidation processes (AOPs) are generally considered as useful treatments for treating organic contaminants, AOPs have been also demonstrated to eliminate emerging contaminants. While AOPs are usually involved with various radicals (e.g., *OH) and reactive oxygen species (ROS), recently SO4^{•-}-involved AOPs also draw growing attention because $SO_4^{\bullet-}$ exhibits higher oxidation power, longer half-lives as well as higher selectivities [7-12]. Therefore, SO₄^{•-}-involved AOPs shall be promising and useful for eliminating Ensulizole. For obtaining $SO_4^{\bullet-}$, monopersulfate (MPS) represents the most common reagent because MPS is commercially available, easily accessible, environmentally benign and inexpensive [13–16]. However, generation of $SO_4^{\bullet-}$ from MPS itself is sluggish and inefficient; thus, MPS must be activated to quickly decompose MPS into SO4. For instance, Zhang and his co-colleagues investigated Ensulizole degradation using NS-CNTs/Cu-Fe₂O₄ coupled with monopersulfate [4]. Besides, Yin et al. prepared MOF-derived cobalt sulfide nanoplates for monopersulfate activation to degrade Ensulizole in water [17].

Among various activation methods, usage of metal catalysts for activating MPS has been validated as the most practical one, and cobalt (Co) is the most capable metal for activating MPS [16,18–22]. However, the direct addition of Co ions into solutions would cause several issues, such as difficult recovery of Co ions, and secondary pollution [23,24]. Therefore, cobalt oxides (e.g., Co₃O₄) are already recognized as the most suitable heterogeneous catalyst to substitute Co ions [19,25,26]. Unfortunately, very few studies have been ever reported by using $\mathrm{Co}_3\mathrm{O}_4$ for activating MPS to degrade Ensulizole. Moreover, since catalytic activities of metal oxide catalysts are strongly associated with their morphologies, surficial properties and other physio-chemical features, nanoscale Co₃O₄ with functional nanostructures would be expected as advantageous catalysts for activating MPS [7,27-31]. Therefore, it would be critical to explore how nanostructured Co3O4 with different morphologies, and characteristics would behave to activate MPS in order to optimize the design and fabrication of Co₃O₄ catalysts for activating MPS in Ensulizole degradation.

Nonetheless, almost no such a study has ever been conducted so far to look into the relationship between shapes, surficial properties and nanostructures of Co_3O_4 materials, and their catalytic activities for MPS. Therefore, the goal of this study is aimed to develop various nanostructured Co_3O_4 and investigate these Co_3O_4 for activating MPS to degrade Ensulizole. Specifically, three Co_3O_4 materials with distinct nanostructures and shapes were fabricated, including Co_3O_4 cone ball (COCB), Co_3O_4 plate lump (COPL), and Co_3O_4 needle sheaf (CONS), and investigated for their catalytic activities of MPS activation.

To conduct Ensulizole degradation experiments, batch-type experiments were employed, in which different parameters influencing Ensulizole degradation were examined including catalyst dosage, MPS dosage, temperatures, pH values and different water sources. The existence of ROS generated from Co_3O_4 -activated MPS was verified by Electron Spin Resonance (ESR). The degradation pathway of Ensulizole is also elucidated based on the detected intermediates. By experimental and theoretical investigations, insightful behaviors and mechanisms of Ensulizole degradation by nanostructured Co_3O_4 +MPS system are further elucidated.

2. Experimental

The preparation procedure of various nanostructured Co_3O_4 is illustrated schematically in Fig. 1(a). In general, Co^{2+} from different cobalt salts would be mixed with carbamide in either ethylene glycol and DI water, and the resulting mixture would be hydrothermally processed, followed by calcination to afford various nanostructured Co_3O_4 . The comprehensive preparation protocols, material characterizations and tests of Ensulizole degradation were given in the supporting information (SI).

3. Results and discussion

3.1. Characterizations of nanostructured Co₃O₄

As these Co_3O_4 catalysts were prepared using different cobalt salts, concentrations of carbamide and solvents, distinct morphologies of Co_3O_4 would be evolved. Fig. 1(b-d) reveal the actual morphologies of the as-prepared Co_3O_4 , whereas Fig. S1 displays precursor images of these Co_3O_4 before the calcination. Specifically, the resultant product displayed in Fig. 1(b) shows a ball-like substance with a microscale diameter. More interestingly, the surface of this ball-like product was comprised of many conic structures whose sizes were a few hundreds of nanometers. Its TEM image (Fig. 2(a)) also indicates that this resultant product was solid with the rounded edge.

Secondly, Fig. 1(c) displays the product derived from the hydrothermal process of using cobalt nitrate and carbamide in ethylene glycol, and its morphology seemed a lump comprised of many plates interpenetrated. The size of this lump was also around 10 μ m; however, the thickness of these plates were a few tens of nanometers. Especially, the inter-penetrating configurations enabled this special product to exhibit voids. Fig. 2(b) also reveals that the plate in this product was very thin, and it was comprised of many fine particles. On the other hand, Fig. 1(d) shows the product from the hydrothermal process of CoCl₂ and carbamide in water exhibited a relatively distinct configuration in which needle-like substances with relatively high aspect ratios were bundled to afford a morphology of sheaf. Fig. 2(c) also validated that these needle-like products were nanoscale with a few tens of nanometers in diameter, and it was also comprised of many fine particles.

To further identify these products, their lattice-resolved HRTEM images were also listed in Fig. 2. Specifically, Fig. 2(d) reveals the lattice-resolved image of the product with the CB morphology, in which the (0–22), and (–202) plane of Co_3O_4 with a *d*-spacing of 0.290 nm at an interfacial angle of 60° , could be detected. This suggests that this resulting product was Co_3O_4 [32]. Its corresponding SAED pattern (Fig. 2(g)) can be well-indexed to Co_3O_4 , confirming that this resultant material was Co_3O_4 with a polycrystalline structure [33,34]. Thus, this resultant material could be confirmed as Co_3O_4 with CB morphology (COCB).

Besides, Fig. 2(e) unveils the lattice-resolved TEM image of the resultant material with the morphology of plate lump, in which the (-111) (*d*-spacing of 0.467 nm) and (2-20) (*d*-spacing of 0.290 nm) crystal planes of Co₃O₄ at an interfacial 45° was detected. This also confirms that the successful formation of Co₃O₄ with the morphology of plate lump (COPL) [35]. Its corresponding SAED pattern could be also well-attributed to the poly-crystalline structure of Co₃O₄. On the other hand, Fig. 2(f) displays the lattice-resolved TEM image of the resulting product with the morphology of needle sheaf (NS), in which the (1-13), and (2-20) planes of Co₃O₄ at an interfacial angle of 65° were detected, indicating the formation of Co₃O₄ with the morphology of NS (CONS) [35]. The corresponding SAED pattern was also well-indexed to the polycrystalline structure of Co₃O₄.

The XRD patterns of these Co_3O_4 catalysts were also determined and summarized in Fig. 3(a), and all these patterns were well-indexed to the reported pattern of Co_3O_4 according to JCPDS #42–1467, validating



Fig. 1. (a) Scheme for preparing nanostructured Co₃O₄; SEM images of (b) COCB, (c) COPL, and (d) CONS (the scale bar is 1 µm).

that these resultant materials were Co_3O_4 with very distinct morphologies. The variation in morphology of nanostructures could be correlated to the anisotropic development of the self-agglomeration of crystallites [36], especially because morphologies of metal oxides would be attributed to the evolution of crystalline nuclei which would be then influenced significantly in the presence of additives (e.g., polymers, and surfactants) [36,37].

Since an additive, carbamide, was particularly employed in the fabrication of Co_3O_4 , carbamide would be readily hydrolyzed to produce carbon dioxide and ammonia [38]. Ammonia would be then transformed to NH_4^+ and OH^- upon exposing to water, and OH^- would react with Co^{2+} to form cobalt hydroxide. Furthermore, NH_4^+ would cause the reaction medium to be basic, and alter rates of cobalt hydroxide precipitate, thus manipulating the morphology. Moreover, the concurrently resulting carbon dioxide would also cause pressures to alter the development of nanocrystallites. Since various cobalt salts were adopted here, the corresponding counter anions of cobalt salts would also serve as template agents to manipulate crystalline nuclei [39]. Therefore, when lower amounts of carbamide were involved (such as COCB and COPL), the resulting morphology of Co_3O_4 would be more like cones and plates. Nevertheless, a high amount of carbamide (such as CONS) was used, needle-like morphology would be afforded.

While these resultant materials were all proven to be Co_3O_4 , it would be worthwhile to further investigate their surface chemistry as they

exhibited very distinct shapes. Thus, XPS full-survey spectra of these Co_3O_4 were measured and displayed in Fig. 3(b), which exhibited very strong signals of Co and O in these materials, and no other noticeable elements could be found. Fig. 4(a) then reveals the Co2p core-level spectra of these nanostructured Co₃O₄ which exhibited very similar patterns with two noticeable broad bands in the ranges of 778-784 eV, and 792-800 eV, attributed to Co2p_{3/2}, and Co2p_{1/2}, respectively [40, 41]. Specifically, the Co2p_{3/2} spectra could be deconvoluted to afford two bands at 780.1, and 781.7 eV, corresponding to Co^{3+} and Co^{2+} [42], respectively, as these species are theoretically comprised in Co3O4. Nonetheless, the fractions of these two species might be influenced owing to slightly different surficial properties of Co3O4. Therefore, the percentages of Co^{2+} , and Co^{3+} of each nanostructured Co_3O_4 was determined in Table S1. Among these three Co_3O_4 , CONS showed a relatively high percentage of Co^{2+} . Since Co^{2+} has been validated as a useful species to activate MPS [18], the relatively abundant Co^{2+} might enable CONS to exhibit a higher catalytic activity of MPS activation.

On the other hand, the O1s core-level spectra of these nanostructured Co_3O_4 are displayed in Fig. 4(b), and these spectra could be also deconvoluted to exhibit three sub-bands located at ca. 529.3, 530.5, and 531.7 eV, corresponding to lattice oxygen (O_L), and oxygen vacancy (O_V), and chemisorbed oxygen (Oc). Since OV has been validated to play a critical role in catalytic processes, and thus the fractions of O_V in these Co_3O_4 (as summarized in Table S1) would be also associated with their



Fig. 2. TEM images of nanostructured Co₃O₄:(a) COCB, (b) COPL, and (c) CONS; HRTEM images of (d) COCB, (b) COPL, and (c) CONS; and SAED patterns of COCB, (b) COPL, and (c) CONS.



Fig. 3. Characteristics of nanostructured Co₃O₄: (a) XRD patterns, and (b) full-survey XPS spectra.

catalytic activities. In particular, the fraction of O_V in CONS was also slightly higher than other two Co_3O_4 , suggesting the surficial characteristics of CONS were slightly distinct from those of these other Co_3O_4 , and might behave differently in activating MPS to degrade Ensulizole.

Besides, Raman spectroscopic analyses of these nanostructured ${\rm Co}_3{\rm O}_4$ were also acquired to probe into their chemical structure in

Fig. S2, and their spectra appeared very comparable to consist of 5 noticeable peaks. In particular, the peaks at 620, 523 as well as 194 cm⁻¹ could be attributed to the F_{2g} symmetry of Co₃O₄ [43,44]. Additionally, the peak at 485 cm⁻¹ would be ascribed to the E_g symmetry of Co₃O₄, while the peak located at 694 cm⁻¹ would be correlated to the A_{1g} symmetry of Co₃O₄ [45,46]. More importantly, as the location of a



Fig. 4. (a) Co2p and (b) O1s core-level XPS spectra of nanostructured Co₃O₄.

certain Raman peak might be shifted owing to structural variation (i.e., defects), a noteworthy feature could be noticed that the A_{1g} symmetry peaks of these three nanostructured Co_3O_4 were slightly distinct as the A_{1g} peak center of CONS was shifted to the left side of the X-axis. This suggests that CONS might exhibit a higher degree of structural defect, which might enable the surface of CONS to be more reactive for improving its catalytic activities [47].

Aside from the aforementioned distinct surficial characteristics, these nanostructured Co_3O_4 essentially showed very different morphologies, and thus their textural properties should be further analyzed. Fig. S3(a) shows N₂ sorption isotherms of these nanostructured Co_3O_4 , and CONS seemed to exhibit the highest N₂ sorption amount, followed by COPL, and then COCB. Therefore, COCB showed a relatively low surface area of 53 m² with a pore volume of 0.20 cm³/g, whereas COPL could show a significantly higher surface of 75 m² with a pore volume of 0.30 cm³/g, and CONS showed a specific surface area of 106 m² with a pore volume of these Co₃O₄ materials would lead to very different textural features, which were anticipated to govern their catalytic behaviors upon exposing to MPS and Ensulizole.

On the other hand, since the study was to investigate the degradation of Ensulizole by MPS in water, another surficial property, surface charge, of these Co_3O_4 would also play an important role in contact with

MPS/Ensulizole. Thus, the surface charges of these Co_3O_4 would be measured and displayed in Fig. S3(b), and generally, their surface charges exhibited a trend that the surface charge would gradually become more negative at higher pH values. In addition, pH_{pzc} of these Co_3O_4 catalysts were ranged from 6 to 8.

3.2. Catalytic degradation of Ensulizole by Co₃O₄-activated MPS

Fig. 5(a) further displays Ensulizole degradation using MPS activated by these nanostructured Co₃O₄. Since Ensulizole might be removed through adsorption to Co₃O₄, adsorptive tests had been also conducted in Fig. 5(a). Nevertheless, almost these Co₃O₄ catalysts were incapable of removing Ensulizole through adsorption. On the other hand, MPS itself was also tested to examine whether the self-decomposition of MPS could degrade Ensulizole. Fig. 5(a) indicates that while Ensulizole could be slightly degraded with C_t/C₀ at 60 min (C₆₀/C₀) approaching 0.8, such an efficiency was quite low, and thus MPS itself was still incapable of removing Ensulizole. Nevertheless, once COCB was combined with MPS, Ensulizole was quickly degraded and C₆₀/C₀ would approach 0.35. Because COCB and MPS were incapable of removing Ensulizole individually, this result suggests that COCB could activate MPS to generate reactive oxygen species to attack Ensulizole.



On the other hand, COPL coupled with MPS was also found to

Fig. 5. Activation of MPS by various nanostructured Co_3O_4 for degradation of Ensulizole: (a) comparisons between adsorption to Co_3O_4 , MPS and Co_3O_4 + MPS, (b) RSE, and (c) rate constants (Co_3O_4 catalysts = 100 mg/L, MPS = 100 mg/L, T = 30 °C).

degrade Ensulizole as C_{60}/C_0 would approach 0.15. This result demonstrated that COPL could also activate MPS to degrade Ensulizole, and COPL seemed to exhibit a higher catalytic activity than COCB to activate MPS. Furthermore, once CONS was combined with MPS, Ensulizole was rapidly degraded and C₆₀/C₀ reached to zero in 10 min. This surprising result not only suggested that CONS could activate MPS for degrading Ensulizole but also the catalytic activity of CONS towards MPS activation. While these nanostructured Co₃O₄ were comprised of almost identical chemical compositions, their activities towards MPS activation were significantly distinct. Since these nanostructured Co₃O₄ catalysts exhibited distinct catalytic activities for activating MPS to degrade Ensulizole, it would be beneficial to measure the mineralization degree of Ensulizole using the total organic carbon (TOC). As depicted in Fig. S4, different TOC results were obtained by these catalysts. Specifically, ca. 65% of TOC was achieved by CONS+MPS system, followed by COPL+MPS (50%) and COCB+MPS (42%), respectively. This result indicated that Ensulizole was certainly decomposed by these nanostructured Co₃O₄ catalysts-activated MPS; however, CONS showed higher mineralization degree compared to COPL and COCB.

For further quantifying the differences in activity of these nanostructured Co_3O_4 for degrading Ensulizole, reaction stoichiometric efficiency (RSE) has been adopted to describe activities of catalysts for activating MPS to degrade organic contaminants through the following equation [48,49]:

$$ReactionStoichiometricEfficiency(RSE) = \frac{Ensulizoledegraded(mol)}{MPSadded(mol)}$$
(1)

The RSE at 60 min obtained by MPS, and combinations of these nanostructured Co_3O_4 and MPS were displayed in Fig. 5. While the RSE of MPS was extremely low as 0.004, RSE of the combinations of these nanostructured Co_3O_4 and MPS were much higher. As CONS could completely eliminate Ensulizole in 60 min, CONS exhibited the highest RSE as 0.027, followed by COPL with a RSE of 0.024, and then COCB with a RSE of 0.018. This comparison indicates that these nanostructured Co_3O_4 were all capable of activating MPS to degrade Ensulizole; nevertheless, CONS showed a much higher capability for activating MPS. On the other hand, while RSE could be an index to reveal degradation efficiency, it would also require another index to interpret the reaction kinetics especially because CONS could lead to the extremely fast degradation of Ensulizole.

To describe the degradation kinetics, the pseudo first-order rate law was then adopted because it has been widely employed for determining the kinetics of pollutant degradation using MPS as follows [50]:

$$\ln(C_t/C_0) = -kt \tag{2}$$

where *k* denotes as the pseudo first-order rate constant. Fig. 5(c) shows the calculated *k* values of Ensulizole degradation by MPS, COCB+MPS, COPL+MPS, and CONS+MPS. Even though COPL+MPS and COCB+MPS could also lead to Ensulizole degradation, their *k* values were actually quite low as 0.0318 and 0.0195 min⁻¹. In contrast, the *k* value obtained by CONS was significantly higher as 0.567 min⁻¹. This kinetic analysis demonstrated that CONS was surpassingly more powerful than COPL and COCB for activating MPS to degrade Ensulizole swiftly.

As nanostructured Co_3O_4 catalysts were all comprised of Co^{2+} , and Co^{3+} species, these Co species can activate MPS to produce ROS ($SO_4^{\bullet-}$, $^{\bullet}OH$) through following equations [51]:

$$Co^{2+}@Co_{3}O_{4} + HSO_{5}^{-} \rightarrow Co^{3+}@Co_{3}O_{4} + SO_{4}^{\bullet-} + OH^{-}$$
 (3)

$$Co^{3+}@Co_{3}O_{4} + HSO_{5}^{-} \rightarrow Co^{2+}@Co_{3}O_{4} + SO_{5}^{\bullet-} + OH^{-}$$
 (4)

$$SO_5^{\bullet-} \rightarrow SO_4^{\bullet-} + 1/2 O_2$$
 (5)

According to these reactions, Co^{2+} seemed to play a more important role than Co^{3+} to quickly generate the more reactive species, $\text{SO}_4^{\bullet-}$ for attacking Ensulizole. As CONS contained a relatively high fraction of

 Co^{2+} , it was expected to enable the quicker decomposition of MPS into $SO_4^{\bullet-}$, thereby leading to the much faster kinetics. On the other hand, CONS also exhibited a higher extent of oxygen vacancy and structural defect, which would also enable the surface of CONS to be more active to react with MPS, resulting in a higher catalytic activity. Moreover, the unique shape of CONS also afforded much more contact surface, which would also allow CONS to quickly react with MPS to achieve the significantly high degradation kinetics.

3.3. Effect of catalyst dosage, MPS dosage and various Ensulizole concentrations

To further explore catalytic behaviors of these nanostructured Co₃O₄, the effects of catalyst and MPS dosages were then examined. Firstly, Fig. S5(a) and (b) reveal the effects of COCB and MPS concentration on Ensulizole degradation, respectively. In general, the degradation efficiency was greatly dependent on COCB and MPS concentration, and much higher COCB and MPS would certainly enhance Ensulizole degradation. Nevertheless, even though either 150 mg/L of COCB or MPS concentration was adopted, COCB could not completely eliminate Ensulizole, suggesting that COCB was certainly a less effective nanostructured Co₃O₄. Besides, Fig. S5(c) shows the effect of variation in COPL dosage on Ensulizole degradation. While COPL seemed much less effective than CONS, the slightly higher COPL dosage (150 mg/L) still enabled the very effective degradation of Ensulizole as $C_{60}/C_0 \sim 0$, with a faster $k = 0.059 \text{ min}^{-1}$ (See Table S2). On the other hand, Fig. S5(d) shows the effect of variation in MPS concentration on Ensulizole degradation, and a much higher MPS concentration (i.e., 150 mg/L) would also enable the almost complete elimination of Ensulizole.

Moreover, Fig. S5(e) shows the effect of CONS dosage, and, interestingly, even though the dosage of CONS was lowered to 50 mg/L, Ensulizole could be still quickly eliminated completely in 10 min. Nevertheless, the higher dosage of CONS would still enable an even faster degradation of Ensulizole as the *k* value at CONS = 150 mg/L would ramp substantially from 0.567 to 0.697 min⁻¹, whereas the *k* at CONS = 50 mg/L was relatively low as 0.434 min⁻¹. This indicates that the higher dosage of catalyst would certainly provide more reactive sites for reacting with MPS, leading to faster kinetics. On the other hand, when a relatively MPS was used (i.e., 50 mg/L), the incomplete degradation of Ensulizole was still observed even though CONS was applied. These comparative results demonstrate that CONS was certainly a much more advantageous Co₃O₄ than the other two Co₃O₄; however, a sufficient amount of MPS was still required to achieve the full elimination of Ensulizole because ROS was produced from MPS rather than Co₃O₄.

3.4. Effects of temperature and pH on Ensulizole degradation

Since environmental conditions, such as temperature, and pH, would considerably influence MPS activation, the effects of temperature and pH on Ensulizole degradation would be then investigated to under how these Co₃O₄ behaved under various conditions. Firstly, Fig. 6(a) shows Ensulizole degradation by COCB-activated MPS at 30, 40 and 50 °C. When the temperature increased from 30° to 40°C, the degradation efficiency was considerably enhanced as Ensulizole was almost completely eliminated in 60 min. In addition, the corresponding k would also increase from 0.0195 to 0.0411 min⁻¹. Furthermore, when temperature increased to 50 °C, Ensulizole could be completely eliminated in 45 min with a much faster $k = 0.1265 \text{ min}^{-1}$. These results validate that the elevated temperature exhibited a significantly positive effect on Ensulizole degradation using COCB-activated MPS.

Fig. 6(d) then displays Ensulizole degradation by COPL at different temperatures. The elevated temperature also led to a huge enhancement in Ensulizole degradation as Ensulizole could be completely eliminated in 45 min at 40 °C, and 30 min at 50 °C. Thus, *k* could be tremendously increased from 0.0318 min⁻¹ at 30 °C to 0.0964 min⁻¹ at 40 °C, and



Fig. 6. Effect of temperature on Ensulizole degradation using MPS activated by nanostructured Co_3O_4 : (a-c) COCB, (d-f) COPL, and (g-i) CONS (Co_3O_4 catalysts = 100 mg/L, MPS = 100 mg/L, T = 30 °C).

 $0.2323\ \text{min}^{-1}$ at 50 °C, respectively, validating the positive effect of higher temperatures on Ensulizole degradation.

As the k value seemed to increase noticeably at higher temperatures by these three Co_3O_4 catalysts, it would be worthwhile to further interpret the relationship between k and temperature, which was then

$$Lnk - lnA = -E_a/RT \tag{6}$$

where A denotes the pre-exponential factor, R means the universal gas constant, T indicates the reaction temperature in Kelvin (K), E_a denotes the activation energy (kJ/mol). Fig. 6(c), (f), and (i) display the plots of 1/T versus k using these three catalysts, respectively, and the data points in these three plots were all well fit by the linear regression, suggesting that the relationship between T and k of Ensulizole degradation could be properly described by the Arrhenius equation.

Moreover, the slope of the fitting curve could be then adopted to calculate activation energy \sim (kJ/mol) as summarized in Table S3. While COCB and COPL showed Ea values in the range of 75–80 kJ/mol, CONS exhibited a tremendously low E_a value of 9.8 kJ/mol, which was even much lower than E_a values by the reported catalysts in literatures. This ascertains that CONS was certainly a promising and unprecedented catalyst for activating MPS to degrade Ensulizole.

On the other hand, the effect of pH on Ensulizole degradation was also examined as shown in Fig. S6. Overall, the effect of pH on Ensulizole degradation using these three Co_3O_4 was quite comparable. The neutral condition (e.g., pH = 7) seemed the most favorable condition for Ensulizole degradation using these Co_3O_4 , while the weakly basic (e.g., pH = 9) would slightly hinder Ensulizole degradation. This might be due to the fact that Ensulizole consists of a sulfonate group, and the basic condition would make the surface of Co_3O_4 more negatively charged, leading to a more intense repulsion between Ensulizole and Co_3O_4 under basic conditions. In addition, when the solution became even more basic (e.g., pH = 11), it would almost suppress Ensulizole degradation. This could be attributed to the fact that the highly basic condition would make MPS more easily decompose without producing radicals, thereby suppressing Ensulizole degradation [52,53].

On the other hand, the acidic environment (e.g., pH = 5) would also cause negative effects on Ensulizole degradation by using these three Co₃O₄, and the strongly acidic condition would cause even more adverse effect as MPS is prone to remaining very stable and less likely being activated under the acidic condition [53].

Nevertheless, CONS would still exhibit much higher degradation efficiencies even under the less favorable conditions, such as the weakly acidic and basic conditions, making it still the most advantageous catalyst among these three nanostructured Co_3O_4 .

3.5. Effect of water sources, and the recyclability of CONS

As CONS was certainly a promising and much more powerful Co_3O_4 than COCB and COPL for activating MPS to degrade Ensulizole, the effect of water sources was also investigated to realize how different types of water would influence Ensulizole degradation by CONS-activated MPS. Fig. 7(a) shows Ensulizole degradation in seawater, tap water and DI water. In the case of seawater, the degradation kinetics seemed to be noticeably influenced as the corresponding k was decreased from 0.567 to 0.062 min⁻¹. This would be due to the fact that seawater contains a high concentration of NaCl as well as other ions, and especially, Cl- would react with $SO_4^{\bullet-}$ to form chloride radical species as follows (Eqs. (7–8)) [54]:

$$\mathrm{Cl}^{-} + \mathrm{SO}_{4}^{\bullet^{-}} \to \mathrm{Cl}^{\bullet} + \mathrm{SO}_{4}^{2^{-}} \tag{7}$$

$$\operatorname{Cl}^{\bullet} + \operatorname{Cl}^{-} \to \operatorname{Cl}_{2}^{\bullet-}$$
 (8)

Unfortunately, the resultant chloride radicals (e.g., Cl[•] (2.4 V), Cl₂^{•-} (2.0 V)) exhibit much lower oxidizing power than $SO_4^{\bullet-}$ (2.5–3.1 V), thereby hindering Ensulizole degradation. Nevertheless, Ensulizole even in seawater could be still completely eliminated by CONS-activated MPS in 120 min. On the other hand, Ensulizole in tap water was also evaluated, and Ensulizole degradation was also slightly influenced because the corresponding k was also decreased to 0.168 min⁻¹. This was because tap water generally contains chlorine which would also



Fig. 7. (a) Effect of water type on Ensulizole degradation; (b) recyclability of CONS for Ensulizole degradation using MPS (CONS catalysts = 100 mg/L, MPS = 100 mg/L, T = 30 °C); (c) SEM image (the scale bar = 1 μ m), and (d) XRD pattern of used CONS.

influence MPS activation and then Ensulizole degradation. Nonetheless, CONS would still enable the complete elimination of Ensulizole, proving the effectiveness of CONS.

Furthermore, the recyclability of CONS was then further evaluated in Fig. 7(b), and Ensulizole could be completely and efficiently eliminated by the used CONS over the continuous five cycles. Moreover, the Co2p core-level spectrum of the used CONS was further analyzed. Fig. S7 shows that the positions of Co species in the used CONS were retained in comparison with the pristine CONS, proving the stability of CONS; however, the proportion of $\text{Co}^{2+}/(\text{Co}^{2+}+\text{Co}^{3+})$ was changed (i.e., 60.11), indicating that there was electron transfer between Co^{2+} and Co^{3+}

during the oxidation reaction. On the other hand, Fig. 7(c-d) also show the appearance and crystalline structure of the used CONS, which were very comparable to those of pristine CONS, demonstrating that CONS was reusable and stable catalyst, making it certainly a promising catalyst for activating MPS to eliminate Ensulizole. Moreover, the leaching test of Co ion during the experimental process was also investigated in this study. According to ICP-MS analysis, only 0.05 mg/L of Co ion has been detected in the solution over 5 degradation cycles, which is substantially lower than the initial concentration of CONS used in the experiment (i. e., 100 mg/L), indicating that Co was merely leached out in the solution during the experimental process. In order to verify the contribution of



Fig. 8. (a) effect of radical inhibitors on Ensulizole degradation using CONS-activated MPS and (b) the calculated corresponding k values. (CONS = 100 mg/L, MPS = 100 mg/L, T = 30 °C, reaction time = 60 min); and (c-d) ESR analysis.

Co ions leached to MPS activation, homogeneous Co ions with the concentration of 0.05 mg/L were then used to activate MPS to degrade Ensulizole. As shown in Fig. S8, the concentration of Ensulizole was negligibly decreased after 60 min, demonstrating that the degradation of Ensulizole was mostly associated with the heterogeneous phase of cobalt in CONS.

3.6. Mechanism of CONS-activated MPS for Ensulizole degradation

To further probe in the mechanism of this promising CONS-activated MPS for Ensulizole degradation, several probing reagents were adopted to provide insights about reactive oxygen species derived from CONS-activated MPS. Firstly, tert-butyl alcohol (BuOH) was adopted as an inhibitor specifically for $^{\circ}$ OH, and Ensulizole degradation by CONS-activated MPS in the presence of BuOH was displayed in Fig. 8(a). Overall, the existence of BuOH caused a slight interference on Ensulizole degradation to decrease the k value from 0.567 to 0.195 min⁻¹, suggesting that $^{\circ}$ OH might exist and result from CONS-activated MPS.

On the other hand, the probing reagent, methanol (MeOH) was then evaluated as MeOH would inhibit both $^{\circ}OH$ and SO₄ $^{\circ-}$, and the degradation of Ensulizole by CONS-activated MPS was significantly suppressed in the presence of MeOH, signifying that MPS would be activated by CONS to generate radicals, including SO₄ $^{\circ-}$ as well as $^{\circ}OH$.

On the other hand, since MPS activation would also lead to the nonradical-route degradation by ${}^{1}O_{2}$ [9,55,56], it was important to verify if ¹O₂ would be also present and derived from CONS-activated MPS. Thus, a specific probing reagent for ¹O₂, NaN₃, was tested, and the corresponding Ensulizole degradation was also noticeably inhibited as its kvalue was decreased to 0.016 min⁻¹, suggesting that ${}^{1}O_{2}$ shall also participate in Ensulizole degradation. Besides, different concentrations of these inhibitors have been further investigated. It can be noticed from Fig. S9 that Ensulizole was still effectively degraded by CONC-activated MPS in the presence of BuOH (5 M), which is similar with 0.5 M of BuOH, suggesting that 0.5 M of TBA was sufficient to quench all produced [•]OH radicals. Moreover, in the presence of 0.5 M of NaN₃, the degradation of Ensulizole was slightly influenced compared to that of 0.1 M. On the other hand, when 5 M of MeOH was used, Ensulizole degradation was certainly inhibited as C_t/C_0 merely approached 0.95. These results indicated that $SO_4^{\bullet-}$, $\bullet OH$, and 1O_2 were generated from CONS+MPS system to involve in the degradation of Ensulizole, and $SO_4^{\bullet-}$ is the dominant species contributing to the degradation of Ensulizole.

To elucidate occurrence of ROS from CONS-activated MPS, ESR analysis was adopted and displayed in Fig. 8(c), and (d). In the case of using DMPO as the spin-trapping compound, the combination of MPS, CONS and DMPO would afford the distinct pattern, which could be well-indexed to the oxidation adduct products of DMPO-SO₄ and DMPO-OH, confirming the occurrence of SO₄^{•-} and •OH radicals from CONS-activated MPS, which contributed to Ensulizole degradation.

Moreover, in the case of using TEMP as the spin-trapping compound (Fig. 8(d)), the combination of MPS, CONS and TEMP would afford a triplet pattern, which would be well-indexed to TEMP- $^{1}O_{2}$, validating the existence of non-radical ROS and its contribution to Ensulizole degradation. Thus, Ensulizole degradation by CONS+MPS would be attributed to several ROS, such as $^{\circ}OH$, SO₄ $^{\bullet-}$, as well as $^{1}O_{2}$ as illustrated in Fig. 8(e).

3.7. Theoretic calculation, and a possible degradation process for Ensulizole

As CONS could lead to highly efficient degradation of Ensulizole, it was critical to investigate how Ensulizole was degraded by CONSactivated MPS. For assisting investigation, the density functional theory (DFT) calculation was utilized to offer important theoretical information about Ensulizole for understanding how Ensulizole would be attacked by these ROS. The details of DFT calculation about Ensulizole was given in the <u>supporting information</u> to optimize the geometry of Ensulizole, and calculate Fukui indices, molecule orbitals (MO) as well as electrostatic potential mapping analysis.

Fig. 9(a) reveals the optimized geometry of Ensulizole with its MOs (Fig. 9(c)). As the semi-transparent green, and red zones signified electron-deficient, and electron-rich zones of Ensulizole. In particular, the HOMO of Ensulizole's imidazole ring would tend to release electrons; consequently, Ensulizole was prone to receiving attacks from electrophilic ROS, such as, [•]OH, and, SO₄^{•-}. Fig. 9(b) also summarizes Fukui indices (i.e., F, F^0 , and F^+) of each site in Ensulizole, and a specific site with a much higher Fukui index (F) was prone to drawing radical attacks. Among these sites, the 6 N site exhibited the highest F- value, followed by 19 C site, 7 C site, 9 C site, and then 11 C site. In addition, sites with relatively high F^0 values would also withdraw non-radical attacks. Therefore, 6 N, 9 C as well 19 C also appeared as relatively active sites to receive attacks. As a result, Ensulizole degradation might be started by attacking N6 site to decompose the entire molecule of Ensulizole into phenolic intermediates, which would receive further attacks on sites, such as C11 or C19 for further decomposition. Besides, the ESP of Ensulizole (Fig. 9(d)) also indicates that N6, C11, and C19 would tend to receive radicals, leading to the decomposition.

Next, for unveiling the degradation pathway of Ensulizole by CONSactivated MPS, its degradation by-products were then analyzed, and several noticeable intermediates were summarized in Table S4. Based on these noticeable intermediates, a possible degradation pathway for Ensulizole by CONS-activated MPS could be then depicted in Fig. 9(e). Initially, Ensulizole would be attacked to break the imidazole ring, resulting in an intermediate, P1, which might be further decomposed to generate P3. On the other hand, the phenolic group connecting to the sulfonate group might be also attacked and opened to generate the intermediate, P2, which would be then further oxidized to generate another intermediate, P4. Both P3 and P4 might be oxidized to produce P5, while P3 could be also oxidized to afford P6. Next, these intermediates, such as P5 and P6, would be further decomposed to produce much smaller molecules, including P7, and eventually to CO_2 and H₂O.

4. Conclusion

For developing an effective Co-based catalyst for activating MPS to degrade one of the most common sunscreen protecting agents, Ensulizole, in water, three Co₃O₄ materials with distinct nanostructures and shapes were fabricated, including Co₃O₄ cone ball (COCB), Co₃O₄ plate lump (COPL), and Co₃O₄ needle sheaf (CONS). Apart from the distinct shapes in these nanostructured Co₃O₄ catalysts, their surficial properties were also noticeably different with different fractions of Co²⁺, and Co³⁺, various oxygen vacancies, textural features and surface defects. Through comparing these three nanostructured Co₃O₄ for activating MPS to degrade Ensulizole, the relationship between shapes, surficial properties and nanostructures of Co₃O₄, and catalytic activities for MPS activation can be unveiled. In particular, since CONS contained a higher fraction of Co²⁺, oxygen vacancies, more surface defects, as well as much higher surface area, CONS exhibited the tremendously higher catalytic activity than COCB and COPL for activating MPS to eliminate Ensulizole completely and rapidly. Moreover, the Ea value of Ensulizole degradation of CONS was significantly low as 9.8 kJ/mol, which was the lowest Ea ever reported in literatures, making CONS a truly promising Co₃O₄ for activating MPS to Ensulizole, possibly owing to its much reactive surface. CONS could also retain its catalytic activities over 5 continuous cycles to efficiently and rapidly degrade Ensulizole. The activation mechanism of MPS by CONS and Ensulizole degradation pathway were also comprehensively elucidated via experimental evidences as well as the theoretical (DFT) calculation to offer insightful information of development of Co-based heterogeneous catalysts for Ensulizole degradation.



Fig. 9. Theoretical analysis for Ensulizole molecule: (a) Ensulizole; (b) Fukui index distributions; (c) molecular orbitals; (d) Electrostatic potential-mapped molecular surface of Ensulizole; (e) A probable degradation process of Ensulizole degradation.

CRediT authorship contribution statement

Wei-Jie Liu: Data curation, Writing – original draft preparation. Young-Kwon Park: Data curation, Writing – original draft preparation. Wei-Hsin Chen: Data curation. Ha Manh Bui: Data curation, Visualization, Investigation. Venkata Subbaiah Munagapati: Data curation, Visualization, Investigation. Duong Dinh Tuan: Writing – reviewing and editing. Jet-Chau Wen: Writing – reviewing and editing. Siming You: Writing – reviewing and editing. Wen Da Oh: Data curation, Writing – original draft preparation. Kun-Yi Andrew Lin: Data curation, Writing – original draft preparation.

Declaration of Competing Interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Appendix A. Supporting information

Supplementary data associated with this article can be found in the online version at doi:10.1016/j.jece.2022.107137.

W.-J. Liu et al.

References

- A. Khamkeaw, M. Phisalaphong, B. Jongsomjit, K.Y.A. Lin, A.C.K. YipSynthesis of mesoporous MFI zeolite via bacterial cellulose-derived carbon templating for fast adsorption of formaldehyde.
- [2] A. Wick, G. Fink, T.A. Ternes, Comparison of electrospray ionization and atmospheric pressure chemical ionization for multi-residue analysis of biocides, UV-filters and benzothiazoles in aqueous matrices and activated sludge by liquid chromatography-tandem mass spectrometry, J. Chromatogr. A 1217 (2010) 2088–2103.
- [3] A. Al-Anazi, W.H. Abdelraheem, C. Han, M.N. Nadagouda, L. Sygellou, M. K. Arfanis, P. Falaras, V.K. Sharma, D.D. Dionysiou, Cobalt ferrite nanoparticles with controlled composition-peroxymonosulfate mediated degradation of 2-phe-nylbenzimidazole-5-sulfonic acid, Appl. Catal. B 221 (2018) 266–279.
- [4] X. Zhang, M. Feng, L. Wang, R. Qu, Z. Wang, Catalytic degradation of 2-phenylbenzimidazole-5-sulfonic acid by peroxymonosulfate activated with nitrogen and sulfur co-doped CNTs-COOH loaded CuFe2O4, Chem. Eng. J. 307 (2017) 95–104.
- [5] L. Hernandez-Leal, H. Temmink, G. Zeeman, C.J. Buisman, Removal of micropollutants from aerobically treated grey water via ozone and activated carbon, Water Res. 45 (2011) 2887–2896.
- [6] K. Fisch, J.J. Waniek, D.E. Schulz-Bull, Occurrence of pharmaceuticals and UVfilters in riverine run-offs and waters of the German Baltic Sea, Mar. Pollut. Bull. 124 (2017) 388–399.
- [7] M.-C. Li, F. Ghanbari, F.-C. Chang, C. Hu, K.-Y.A. Lin, Y. Du, Enhanced degradation of 5-sulfosalicylic acid using peroxymonosulfate activated by ordered porous silicaconfined Co3O4 prepared via a solvent-free confined space strategy, Sep. Purif. Technol. (2020), 116972.
- [8] W. Li, S. Li, Y. Tang, X. Yang, W. Zhang, X. Zhang, H. Chai, Y. Huang, Highly efficient activation of peroxymonosulfate by cobalt sulfide hollow nanospheres for fast ciprofloxacin degradation, J. Hazard. Mater. 389 (2020), 121856.
- [9] P. Liang, C. Zhang, X. Duan, H. Sun, S. Liu, M.O. Tade, S. Wang, An insight into metal organic framework derived N-doped graphene for the oxidative degradation of persistent contaminants: formation mechanism and generation of singlet oxygen from peroxymonosulfate, Environ. Sci.: Nano 4 (2017) 315–324.
- [10] K.-Y.A. Lin, H.-A. Chang, Zeolitic imidazole framework-67 (ZIF-67) as a heterogeneous catalyst to activate peroxymonosulfate for degradation of Rhodamine B in water, J. Taiwan Inst. Chem. Eng. 53 (2015) 40–45.
- [11] K.-Y.A. Lin, J.-T. Lin, A.P. Jochems, Oxidation of amaranth dye by persulfate and peroxymonosulfate activated by ferrocene, J. Chem. Technol. Biotechnol. 92 (2017) 163–172.
- [12] K.-Y.A. Lin, Z.-Y. Zhang, Degradation of bisphenol a using peroxymonosulfate activated by one-step prepared sulfur-doped carbon nitride as a metal-free heterogeneous catalyst, Chem. Eng. J. 313 (2017) 1320–1327.
- [13] P. Hu, M. Long, Cobalt-catalyzed sulfate radical-based advanced oxidation: a review on heterogeneous catalysts and applications, Appl. Catal. B: Environ. 181 (2016) 103–117.
- [14] Y. Guo, D.C.W. Tsang, X. Zhang, X. Yang, Cu(II)-catalyzed degradation of ampicillin: effect of pH and dissolved oxygen, Environ. Sci. Pollut. Res. 25 (2018) 4279–4288.
- [15] S.-N. Zhu, C. Wang, A.C.K. Yip, D.C.W. Tsang, Highly effective degradation of sodium dodecylbenzene sulphonate and synthetic greywater by Fenton-like reaction over zerovalent iron-based catalyst, Environ. Technol. 36 (2015) 1423–1432.
- [16] M.-H. Li, K.-Y.A. Lin, M.-T. Yang, B.X. Thanh, D.C.W. Tsang, Prussian Blue Analogue-derived co/fe bimetallic nanoparticles immobilized on S/N-doped carbon sheet as a magnetic heterogeneous catalyst for activating peroxymonosulfate in water, Chemosphere 244 (2020), 125444.
- [17] J.-Y. Yin, H. Wang, K.-P. Yu, J. Lee, K.-Y.A. Lin, Degradation of sunscreen agent 2phenylbenzimidazole-5-sulfonic acid using monopersulfate activated by MOFderived cobalt sulfide nanoplates, J. Water Process Eng. 44 (2021), 102282.
- [18] G.P. Anipsitakis, E. Stathatos, D.D. Dionysiou, Heterogeneous activation of oxone using Co3O4, J. Phys. Chem. B 109 (2005) 13052–13055.
- [19] D.D. Tuan, C. Hung, W. Da Oh, F. Ghanbari, J.-Y. Lin, K.-Y. Andrew Lin, Porous hexagonal nanoplate cobalt oxide derived from a coordination polymer as an effective catalyst for activating oxone in water, Chemosphere (2020), 127552.
- [20] M.-W. Zhang, M.-T. Yang, S. Tong, K.-Y.A. Lin, Ferrocene-modified iron-based metal-organic frameworks as an enhanced catalyst for activating oxone to degrade pollutants in water, Chemosphere 213 (2018) 295–304.
- [21] K.-Y.A. Lin, T.-Y. Lin, Degradation of acid azo dyes using oxone activated by cobalt titanate perovskite, Water, Air, Soil Pollut. 229 (2018) 10.
- [22] K.-Y.A. Lin, J.-T. Lin, X.-Y. Lu, C. Hung, Y.-F. Lin, Electrospun magnetic cobaltembedded carbon nanofiber as a heterogeneous catalyst for activation of oxone for degradation of Amaranth dye, J. Colloid Interface Sci. 505 (2017) 728–735.
- [23] Q. Yang, H. Choi, S.R. Al-Abed, D.D. Dionysiou, Iron–cobalt mixed oxide nanocatalysts: heterogeneous peroxymonosulfate activation, cobalt leaching, and ferromagnetic properties for environmental applications, Appl. Catal. B: Environ. 88 (2009) 462–469.
- [24] C. Cai, H. Zhang, X. Zhong, L. Hou, Ultrasound enhanced heterogeneous activation of peroxymonosulfate by a bimetallic Fe–Co/SBA-15 catalyst for the degradation of Orange II in water, J. Hazard. Mater. 283 (2015) 70–79.
- [25] X. Chen, J. Chen, X. Qiao, D. Wang, X. Cai, Performance of nano-Co3O4/ peroxymonosulfate system: kinetics and mechanism study using acid orange 7 as a model compound, Appl. Catal. B: Environ. 80 (2008) 116–121.
- [26] C. Wang, P. Shi, X. Cai, Q. Xu, X. Zhou, X. Zhou, D. Yang, J. Fan, Y. Min, H. Ge, W. Yao, Synergistic effect of Co3O4 nanoparticles and graphene as catalysts for

Journal of Environmental Chemical Engineering 10 (2022) 107137

peroxymonosulfate-based orange II degradation with high oxidant utilization efficiency, J. Phys. Chem. C. 120 (2016) 336–344.

- [27] C.Y. Ma, Z. Mu, J.J. Li, Y.G. Jin, J. Cheng, G.Q. Lu, Z.P. Hao, S.Z. Qiao, Mesoporous Co3O4 and Au/Co3O4 Catalysts for low-temperature oxidation of trace ethylene, J. Am. Chem. Soc. 132 (2010) 2608–2613.
- [28] Y. Sun, J. Liu, J. Song, S. Huang, N. Yang, J. Zhang, Y. Sun, Y. Zhu, Exploring the effect of Co3O4 nanocatalysts with different dimensional architectures on methane, Combustion 8 (2016) 540–545.
- [29] X. Xie, Y. Li, Z.-Q. Liu, M. Haruta, W. Shen, Low-temperature oxidation of CO catalysed by Co3O4 nanorods, Nature 458 (2009) 746–749.
- [30] D.D. Tuan, C. Hu, E. Kwon, Y. Du, K.-Y.A. Lin, Coordination polymer-derived porous Co3O4 nanosheet as an effective catalyst for activating peroxymonosulfate to degrade sulfosalicylic acid, Appl. Surf. Sci. 532 (2020), 147382.
- [31] W.-C. Yun, K.-Y.A. Lin, W.-C. Tong, Y.-F. Lin, Y. Du, Enhanced degradation of paracetamol in water using sulfate radical-based advanced oxidation processes catalyzed by 3-dimensional Co3O4 nanoflower, Chem. Eng. J. 373 (2019) 1329–1337.
- [32] X.-Y. Yu, Q.-Q. Meng, T. Luo, Y. Jia, B. Sun, Q.-X. Li, J.-H. Liu, X.-J. Huang, Facetdependent electrochemical properties of Co3O4 nanocrystals toward heavy metal ions, Sci. Rep. 3 (2013) 2886.
- [33] G. Cheng, T. Kou, J. Zhang, C. Si, H. Gao, Z. Zhang, O22-/O- functionalized oxygendeficient Co3O4 nanorods as high performance supercapacitor electrodes and electrocatalysts towards water splitting, Nano Energy 38 (2017) 155–166.
- [34] D. Wang, Q. Wang, T. Wang, Morphology-controllable synthesis of cobalt oxalates and their conversion to mesoporous Co3O4 nanostructures for application in supercapacitors, Inorg. Chem. 50 (2011) 6482–6492.
- [35] Q. Ren, S. Mo, R. Peng, Z. Feng, M. Zhang, L. Chen, M. Fu, J. Wu, D. Ye, Controllable synthesis of 3D hierarchical Co3O4 nanocatalysts with various morphologies for the catalytic oxidation of toluene, J. Mater. Chem. A 6 (2018) 498–509.
- [36] Z. Sun, T. Liao, L. Kou, Strategies for designing metal oxide nanostructures, Sci. China Mater. 60 (2017) 1–24.
- [37] Z.H. Ibupoto, S. Elhag, M.S. AlSalhi, O. Nur, M. Willander, Effect of urea on the morphology of Co3O4 nanostructures and their application for potentiometric glucose biosensor, Electroanalysis 26 (2014) 1773–1781.
- [38] D. Guragain, C. Zequine, T. Poudel, D. Neupane, R.K. Gupta, S.R. Mishra, Influence of urea on the synthesis of NiCo2O4 nanostructure: morphological and electrochemical studies, J. Nanosci. Nanotechnol. 20 (2020) 2526–2537.
- [39] T. Fuchigami, R. Kimata, M. Haneda, K.-i Kakimoto, Complex three-dimensional Co3O4 nano-raspberry: highly stable and active low-temperature CO oxidation catalyst, Nanomaterials 8 (2018) 662.
- [40] H.-K. Lai, Y.-Z. Chou, M.-H. Lee, K.-Y.A. Lin, Coordination polymer-derived cobalt nanoparticle-embedded carbon nanocomposite as a magnetic multi-functional catalyst for energy generation and biomass conversion, Chem. Eng. J. 332 (2018) 717–726.
- [41] K.-Y.A. Lin, B.-J. Chen, Magnetic carbon-supported cobalt derived from a Prussian blue analogue as a heterogeneous catalyst to activate peroxymonosulfate for efficient degradation of caffeine in water, J. Colloid Interface Sci. 486 (2017) 255–264.
- [42] L.-L. Feng, M. Fan, Y. Wu, Y. Liu, G.-D. Li, H. Chen, W. Chen, D. Wang, X. Zou, Metallic Co9S8 nanosheets grown on carbon cloth as efficient binder-free electrocatalysts for the hydrogen evolution reaction in neutral media, J. Mater. Chem. A 4 (2016) 6860–6867.
- [43] S. Zhao, F. Hu, J. Li, Hierarchical core-shell Al2O3@Pd-CoAlO microspheres for low-temperature toluene combustion, ACS Catal. 6 (2016) 3433–3441.
- [44] B. de Rivas, R. López-Fonseca, C. Jiménez-González, J.I. Gutiérrez-Ortiz, Synthesis, characterisation and catalytic performance of nanocrystalline Co3O4 for gas-phase chlorinated VOC abatement, J. Catal. 281 (2011) 88–97.
- [45] Q. Liu, L.-C. Wang, M. Chen, Y. Cao, H.-Y. He, K.-N. Fan, Dry citrate-precursor synthesized nanocrystalline cobalt oxide as highly active catalyst for total oxidation of propane, J. Catal. 263 (2009) 104–113.
- [46] X. Wang, Y. Liu, T. Zhang, Y. Luo, Z. Lan, K. Zhang, J. Zuo, L. Jiang, R. Wang, Geometrical-site-dependent catalytic activity of ordered mesoporous Co-based spinel for benzene oxidation: in situ DRIFTS study coupled with Raman and XAFS spectroscopy, ACS Catal. 7 (2017) 1626–1636.
- [47] L. Hu, Q. Peng, Y. Li, Selective synthesis of Co3O4 nanocrystal with different shape and crystal plane effect on catalytic property for methane combustion, J. Am. Chem. Soc. 130 (2008) 16136–16137.
- [48] N.H. Trang, E. Kwon, G. Lisak, C. Hu, K.-Y. Andrew Lin, Cobalt ferrite nanoparticleloaded nitrogen-doped carbon sponge as a magnetic 3D heterogeneous catalyst for monopersulfate-based oxidation of salicylic acid, Chemosphere 267 (2021), 128906.
- [49] Y. Bao, W.-D. Oh, T.-T. Lim, R. Wang, R.D. Webster, X. Hu, Elucidation of stoichiometric efficiency, radical generation and transformation pathway during catalytic oxidation of sulfamethoxazole via peroxymonosulfate activation, Water Res. 151 (2019) 64–74.
- [50] Q.F. Wang, Y.S. Shao, N.Y. Gao, W.H. Chu, J.X. Chen, X. Lu, Y.P. Zhu, N. An, Activation of peroxymonosulfate by Al2O3-based CoFe2O4 for the degradation of sulfachloropyridazine sodium: Kinetics and mechanism, Sep Purif. Technol. 189 (2017) 176–185.
- [51] P.D. Hu, M.C. Long, Cobalt-catalyzed sulfate radical-based advanced oxidation: a review on heterogeneous catalysts and applications, Appl. Catal. B-Environ. 181 (2016) 103–117.
- [52] A. Rastogi, S.R. Al-Abed, D.D. Dionysiou, Sulfate radical-based ferrous-peroxymonosulfate oxidative system for PCBs degradation in aqueous and sediment systems, Appl. Catal. B: Environ. 85 (2009) 171–179.

W.-J. Liu et al.

- [53] W. Guo, S. Su, C. Yi, Z. Ma, Degradation of antibiotics amoxicillin by Co3O4catalyzed peroxymonosulfate system, Environ. Prog. Sustain. Energy 32 (2013) 193–197.
- [54] C. Tan, N. Gao, Y. Deng, J. Deng, S. Zhou, J. Li, X. Xin, Radical induced degradation of acetaminophen with Fe3O4 magnetic nanoparticles as heterogeneous activator of peroxymonosulfate, J. Hazard. Mater. 276 (2014) 452–460.
- [55] R. Luo, M. Li, C. Wang, M. Zhang, M.A. Nasir Khan, X. Sun, J. Shen, W. Han, L. Wang, J. Li, Singlet oxygen-dominated non-radical oxidation process for efficient degradation of bisphenol a under high salinity condition, Water Res. 148 (2019) 416–424.
- [56] S. Yang, P. Wu, J. Liu, M. Chen, Z. Ahmed, N. Zhu, Efficient removal of bisphenol a by superoxide radical and singlet oxygen generated from peroxymonosulfate activated with Fe0-montmorillonite, Chem. Eng. J. 350 (2018) 484–495.